



Chemical Analysis

Ca (%)	Si (%)	Al (%)	C (%)	P (%)	S (%)	Fe (%)
> 30	55-65	< 1.5	< 1	< 0.05	< 0.05	Balanced

Physical properties

Diameter (mm)	Fill rate (gr/m)	Thickness of plate (mm)	Direction	Weight (Kg)
13 ± 0.3	230 ± 10	0.35 – 0.4	Horizontal	1250
13 ± 0.3	230 ± 10	0.35 – 0.4	Vertical	1250

Dimensions

Direction Dim (mm)	Vertical	Horizontal
A	900 ± 20	900 ± 20
D1	1200 ± 20	1200 ± 20
D2	700 ± 20	700 ± 20

